



Preliminary Datasheet

Quality:	ACB 145	
Color:	white	
Coating:	solvent free, 1 side	
Material basis:	extremely tough, 1-side clay coated, woodfree, moisture-stabilized for extreme dimensional stability	
Weight:	136 +/- 8 g/m ²	
Caliper:	140 +/- 9 µm	
Tensile strength MD:	140 N/20 mm	
Tensile strength CD:	80 N/20 mm	
Elongation at break MD:	1,7 +/- 0,6 %	
Elongation at break CD:	4,0 +/- 1,1 %	
Moisture:	5,0 +/- 1,0%	
Release value (LF-925):	0,15 +/- 0,05 N/25 mm	(FTM 10, Tesa 4651)
Special production:	- special release values	
Shelf life:	1 year	(at 22 °C / 50% RH)

The above mentioned information is based on laboratory tests and practical experiences. Due to the various possibilities of applications we cannot give any guarantee. Only own tests can give security as the use of the material for the actual purpose.

Issue date: 01-07-2008